



FOAM SPILL CONTAINMENT



- Durable foam logs allow vehicles to drive over them and still retain their original shape
- Heavy-duty 30 ounce fabric is appropriate for water, hydrocarbons, and most chemicals
- Foam logs are covered with a fuel resistant polyethylene
- Easily emptied through $\frac{3}{4}$ " drains



- Clean and store for repeated use
- Includes patch kit and 20 extra zip ties
- Available in Black or Polyurea
- Meets U.S. regulations for spill containment
- Also available in -60°F rated liner material
- Custom Sizes Available
- 4" and 6" heights available

Dimensions	Capacity	Colors
5' x 5' x 4"	62 gal	Black or Polyurea
5' x 5' x 6"	93 gal	Black or Polyurea
8' x 8' x 4"	160 gal	Black or Polyurea
8' x 8' x 6"	239 gal	Black or Polyurea
10' x 10' x 4"	249 gal	Black or Polyurea
10' x 10' x 6"	374 gal	Black or Polyurea
12' x 36' x 4"	1,077 gal	Black or Polyurea
12' x 36' x 6"	1,616 gal	Black or Polyurea
14' x 54' x 4"	1,885 gal	Black or Polyurea
14' x 54' x 6"	2,828 gal	Black or Polyurea



FOAM SPILL CONTAINMENT

Gallons and dims by wall size

Width	Length	4" / Gallons	4"/Outside Dims	6" / Gallons	6"/Outside Dims
10'	10'	246	10'-8" X 10'-8"	374	11' X 11'
10'	20'	493	10'-8" X 20'-8"	748	11' X 21'
12'	36'	1066	14'-8" X 36'-8"	1,616	15' X 37'
14'	54'	1866	14'-8" X 54'-8"	2,828	15' X 55'

Fabric: 30 oz. Hydrocarbon / chemical resistant

Standard Colors: Black

		US	Metric
Base Fabric Type		Polyester	
Base Fabric Weight (nominal)		8 oz/yd ²	270 g/m ²
Thickness		36 mils min	0.91 mm
Weight		30.0+ _ 2 oz/yd ²	1020+ _ 70 g/m ²
Tear Strength, Tongue D751B		120/120 lb min	534/534 N min
Breaking Yield Strength ASTM D 751, Grab Tensile, Procedure		625/600 lb min	2780/2670 N min
Low Temperature ASTM D 2136,		Pass @ -40 F	Pass @ -40 C
Dimensional Stability ASTM D 1204, 212 F- 1 hr		2.5% max each direction	
Adhesion - Heat Sealed Seam ASTM D 751, Dielectric Weld		25 lb/2 in min	111 N/5 cm min
Bursting Strength ASTM D 751, Ball Tip		1000 lb min	4450 N
Hydrostatic Resistance ASTM D 751, Method A		800 psi min	540 N/sq cm min
Blocking Resistance ASTM D 751, 180 F/82 C		# 2 Rating max	
Resistanc		8000 hrs	
Puncture Resistance ASTM D 4833		220 lb min	1110 N min